

»speedfit« and »sharkbite« series – coils.

Plastic pipe made of LLDPE/LDPE with approval according to DVGW work sheet W270, KTW, NSF and WRAS. LLDPE/LDPE pipes are suitable for potable water uses (cold water) with a maximum chlorine content of 4 parts per million (ppm).

Warm water above 20 °C and / or pressurising above the given maximum reduces the lifetime of this material. Also, placement in direct sunlight should be avoided.

Operating temperature -20 °C to 65 °C

Plastic pipe, LLDPE/LDPE - black

Art. No.	Type No.	Tube O.D. mm	Tube I.D. mm	Working pressure bar	Reel length m	Bending radius min. mm	Material
136361	97.04-100	4	2.5	-0.95 to 15	100	25	LLDPE
136362	97.06-100	6	4	-0.95 to 15	100	25	LLDPE
136363	97.08-100	8	6	-0.95 to 10	100	30	LLDPE
136364	97.10-100	10	7	-0.95 to 10	100	32	LLDPE
136365	97.12-100	12	9	-0.95 to 10	100	63	LLDPE
136366	97.15-100	15	11.5	-0.95 to 10	100	85	LLDPE
136367	97.22-50	22	17.7	-0.95 to 6	50	150	LDPE



97.15-100